



Global Synthetics



www.globalsynthetics.com.au

Sydney 8/28 Oramzi Rd, Cnr Rawson, NSW 2145
Phone: 02 9631 0744 • Fax 02 9631 0755

Australian Company – Global Expertise

Brisbane 44 Telford St, Virginia, QLD 4014
Phone: 07 3865 7000 • Fax 07 3865 4444

info@globalsynthetics.com.au

Perth 17 Church Rd, Maddington, WA 6109
Phone: 08 9459 4300 • Fax 08 9459 4311

NAUE GmbH & Co. KG
Windmuehlenweg 4
47906 Kempen/Toenisberg, Germany

Phone: +49 2845 808-0 • Fax: +49 2845 808-116
E-Mail: info@naue.com • Internet: www.naue.com

Technical Data 2159
Carbofol® Type HDPE 406 GM13
MegaFriction / MegaFriction
acc. to GM 13
Values tested in the structured area

dated: 20.01.2010

Property	Test Method ASTM	Unit				Testing Frequency (minimum)
Thickness (nom. – 5 %)						
- 10% Lowest individual for 8 out of 10 values	D 5994	mm	1,5	2,0	2,5	per roll
-15% Lowest individual for any of the 10 values						
Width	/	m	5,1	5,1	5,1	per day
Asperity height	D 7466	mm	≥ 0,9	≥ 0,9	≥ 0,9	Every 2 nd roll
Density	D 1505 / D 792	g/cm ³	0,942	0,942	0,942	90,000 kg
Tensile strength at yield	D 6693	kN/m	23	30	38	9,000 kg
Elongation at yield	D 6693	%	12	12	12	9,000 kg
Tensile strength at break	D 6693	kN/m	24	32	40	9,000 kg
Elongation at break	D 6693	%	300	300	300	9,000 kg
Tear resistance	D 1004	N	200	280	350	20,000 kg
Puncture resistance	D 4833	N	600	700	820	20,000 kg
Carbon black content	D 1603	%	2-3	2-3	2-3	9,000 kg
Carbon black dispersion	D 5596	Category	1-2	1-2	1-2	20,000 kg
Oxidative Induction Time (OIT) a) standard OIT	D 3895	min	100	100	100	90,000 kg
Oven Aging at 85°C (retrained after 90 days) a) standard OIT	D 5721 D 3895	%	55	55	55	per each formulation
UV Resistance a) standard OIT	D 3895	%	50	50	50	per each formulation

Values tested in the outside edge welding zones

NCTL - Test* Stress crack resistance	D 5397	hour	400	GRI GM-10
---	--------	------	-----	-----------

file: 2159 - 406 mf-mf GM13 struct. Rev.13 eng.doc

remark:

*requirement GM13 : 300h

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to change without prior notice.